



CONSUMER PRODUCTS SERVICES DIVISION

## AAKRON RULE CORP.

**Technical Report:** (5112)130-0252  
Date Received: May 09, 2012

May 16, 2012  
Page 1 of 3

NICK SARRATORI  
AAKRON RULE CORP.  
8 INDIANOLA AVE.  
AKRON, NY 14001  
UNITED STATES

Sample Description:	17OZ MOOD STADIUM CUPS	PO No.:	15717
Manufacturer:	AAKRON RULE	Style:	N/A
Buyer:	N/A	Country of Destination:	N/A
Country of Origin:	UNITED STATES	SKU No.:	N/A
Color:	N/A		
Protocol No.:	N/A		

### EXECUTIVE SUMMARY:

The sample(s) MEETS the following requirement(s):

- The limits set forth in Title 21, Code of Federal Regulations (CFR), Section 177.1520 "Indirect Food Additives: Polymers - Olefin Polymers - Polypropylene" paragraph (c)1.1, for use as articles or components of articles intended for use in contact with food.

BVCPS Buffalo Contact Information for this Report:

Administrative Questions:	Michelle Korkowicz	Phone: 716-505-3583	<a href="mailto:michelle.korkowicz@us.bureauveritas.com">michelle.korkowicz@us.bureauveritas.com</a>
Technical Questions:	Alison Tuzzolino	Phone: 716-505-3434	<a href="mailto:alison.tuzzolino@us.bureauveritas.com">alison.tuzzolino@us.bureauveritas.com</a>

Bureau Veritas  
Consumer Products Services, Inc.

Alison Tuzzolino, Product Chemist  
Analytical Services

/gs



**RESULTS:**

FDA FOOD SIMULATING SOLVENT EXTRACTIVES  
POLYMERS: OLEFIN POLYMERS - POLYPROPYLENE

The samples were tested according to the Food and Drug Administration (FDA), Title 21, Code of Federal Regulations (CFR), Section 177.1520 "Indirect Food Additives: Polymers - Olefin Polymers - Polypropylene."

Sample Description: Frosted orange, frosted blue, and frosted red plastic cups

Condition of Use: For use as articles or components of articles intended for use in contact with food

PARAMETER	RESULT	REQUIREMENT	CONCLUSION
- Density	0.899 g/cc	0.880 - 0.913 g/cc	Pass
- Melting Point	168.8 °C	160°C - 180°C	Pass
- n-Hexane Extractables	3.2 %	≤6.4%	Pass
- Solubles in Xylene	4.7 %	≤9.8%	Pass
g/cc = grams per cubic centimeter ≤ = Less than or equivalent to * = Average of duplicate analyses LT = Less Than			

Sample Description: Frosted purple, pink, and blue blue plastic cups

Condition of Use: For use as articles or components of articles intended for use in contact with food

PARAMETER	RESULT	REQUIREMENT	CONCLUSION
- Density	0.883 g/cc	0.880 - 0.913 g/cc	Pass
- Melting Point	168.1 °C	160°C - 180°C	Pass
- n-Hexane Extractables	3.1 %	≤6.4%	Pass
- Solubles in Xylene	4.7 %	≤9.8%	Pass
g/cc = grams per cubic centimeter ≤ = Less than or equivalent to * = Average of duplicate analyses LT = Less Than			

Sample Description: Yellow, orange, and frosted yellow plastic cups

Condition of Use: For use as articles or components of articles intended for use in contact with food

PARAMETER	RESULT	REQUIREMENT	CONCLUSION
- Density	0.883 g/cc	0.880 - 0.913 g/cc	Pass
- Melting Point	168.5 °C	160°C - 180°C	Pass
- n-Hexane Extractables	3.4 %	≤6.4%	Pass
- Solubles in Xylene	4.8 %	≤9.8%	Pass
g/cc = grams per cubic centimeter ≤ = Less than or equivalent to * = Average of duplicate analyses LT = Less Than			

**EXHIBIT # 1**



**SAMPLE PRODUCT**