

TEST REPORT

Test Report # 19H-009612 Date of Report Issue: January 15, 2020
Date of Sample Received: December 30, 2019 Pages: Page 1 of 21

CLIENT INFORMATION:

Company: Hit Promotional Products
Recipient: Nathan Cotter
Recipient Email: ncotter@hitpromo.net



SAMPLE INFORMATION:

Description: 16 Oz. Navajo Mug
Assortment: 4 colors Purchase Order Number: 346070
SKU No.: 8155 Agent: Growth-Sonic
Factory No.: 127791 Country of Origin: China
Country of Distribution: United States Labeled Age Grade: -
Quantity Submitted: 21 pcs per style Recommended Age Grade: -
Testing Period: 12/30/2019 – 01/15/2020 Tested Age Grade: -

OVERALL RESULT:

 **PASS**

Refer to page 2 for test result summary and appropriate notes.

QIMA Testing (HK) Limited

Loska Yeung Lok Ka
Assistant Manager, Chemical Laboratory

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Glass and Ceramic Materials ^ϕ
PASS	California Proposition 65, Total Lead in Glass and Ceramic Materials ^ϕ
PASS	California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior
PASS	FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior
PASS	California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim
PASS	California Proposition 65 Case No. CGC-04-436429, Lead and Cadmium from Beverage Products – External Decoration

DETAILED RESULTS:

CPSIA Section 101, Total Lead in Glass and Ceramic Materials

Test Method: In-House Method^ϕ
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	20	21	23	ND	---	100
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

DETAILED RESULTS:

California Proposition 65, Total Lead in Glass and Ceramic Materials

Test Method: In-House Method^ϕ
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	20	21	23	ND	---	100
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

DETAILED RESULTS:

California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5A	5B	5C	5D	5E	5F	5G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	450	450	450	450	450	450	450
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	5H	5I	5J	5K	5L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

DETAILED RESULTS:

California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	6A	6B	6C	6D	6E	6F	6G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	450	450	450	450	450	450	450
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	6H	6I	6J	6K	6L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

DETAILED RESULTS:

California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	7A	7B	7C	7D	7E	7F	7G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	450	450	450	450	450	450	450
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	7H	7I	7J	7K	7L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

DETAILED RESULTS:

California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	8A	8B	8C	8D	8E	8F	8G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	450	450	450	450	450	450	450
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	8H	8I	8J	8K	8L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5A	5B	5C	5D	5E	5F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	6A	6B	6C	6D	6E	6F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	PASS	

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	7A	7B	7C	7D	7E	7F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	8A	8B	8C	8D	8E	8F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	450	450	450	450	450	450		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

	Category	Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

DETAILED RESULTS:

California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim

Test Method: ASTM C927-80(2019)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	9A	9B	9C	9D	9E	9F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	190	190	190	190	190	190	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	10A	10B	10C	10D	10E	10F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	190	190	190	190	190	190	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 LT = Less than
 ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

DETAILED RESULTS:

California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim

Test Method: ASTM C927-80(2019)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	11A	11B	11C	11D	11E	11F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	190	190	190	190	190	190	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Specimen No.	12A	12B	12C	12D	12E	12F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	190	190	190	190	190	190	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 LT = Less than
 ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

DETAILED RESULTS:

California Proposition 65 Case No. CGC-04-436429, Lead and Cadmium from Beverage Products – External Decoration

Test Method: NIOSH Method 9100
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	13	14	15	16	---	Limit (µg/article)
Test Item	Result (µg/article)	Result (µg/article)	Result (µg/article)	Result (µg/article)	Result (µg/article)	
Cadmium (Cd)	ND	ND	ND	ND	---	1.0
Lead (Pb)	ND	ND	ND	ND	---	1.0
Conclusion	PASS	PASS	PASS	PASS	---	

Note:
 µg/article = Micrograms per article
 LT = Less than
 ND = Not detected (Reporting Limit = 0.4 µg/article)

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Multicolor printed beige ceramic	Body of mug (blue style)
2	Multicolor printed beige ceramic	Body of mug (brown style)
3	Multicolor printed beige ceramic	Body of mug (green style)
4	Multicolor printed beige ceramic	Body of mug (khaki style)
5	Multicolor printed beige ceramic	Interior of mug (blue style)
6	Multicolor printed beige ceramic	Interior of mug (brown style)
7	Multicolor printed beige ceramic	Interior of mug (green style)
8	Multicolor printed beige ceramic	Interior of mug (khaki style)
9	Multicolor printed beige ceramic	Lip & rim of mug (blue style)
10	Multicolor printed beige ceramic	Lip & rim of mug (brown style)
11	Multicolor printed beige ceramic	Lip & rim of mug (green style)
12	Multicolor printed beige ceramic	Lip & rim of mug (khaki style)
13	Multicolor printed beige ceramic	External decoration of mug (blue style)
14	Multicolor printed beige ceramic	External decoration of mug (brown style)
15	Multicolor printed beige ceramic	External decoration of mug (green style)
16	Multicolor printed beige ceramic	External decoration of mug (khaki style)

SAMPLE PHOTO:



-End Report-