



中国认可
国际互认
检测
TESTING
CNAS L6478



TEST REPORT

Reference No. : WTF19F05028890C

Applicant : Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

Manufacturer : 111999

Sample Name : Ceramic mug w/ lid and sleeve, Double wall travel cup, Chalk tumbler in double wall

Model No. : MO7683, MO8130, MO8662, CX1380

Test Requested : In accordance with Council of Europe Resolution AP(2004)5, Council of Europe Resolution 84/500/EC (2005/31/EC) and Regulation (EC) No 1935/2004.

Test Conclusion : **Pass** (Please refer to next pages for details)

Date of Receipt sample : 2019-05-09

Date of Test : 2019-05-09 to 2019-05-16

Date of Issue : 2019-05-17

Test Result : Please refer to next page (s)

Remarks:

The results shown in this test report refer only to the sample(s) tested, this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

Prepared By:

Waltek Services (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

Abby Zhou

Abby.Zhou / Project Engineer

Approved by:



Dino Zhang

Dino Zhang / Lab Manager

**Test Results:****1. Overall Migration Test**

Food Simulant	Test Condition	Result (mg/dm ²)	MDL (mg/dm ²)	Limit (mg/dm ²)
		No.1		
3% Acetic Acid	70°C for 2 hours	ND	3	10
50% Ethanol	70°C for 2 hours	ND	3	10

Note:

1. Test method: With reference to BS EN 1186-1: 2002, BS EN 1186-3: 2002, BS EN 1186-9: 2002 and BS EN1186-14: 2002.
2. "mg/dm²" = milligram per square decimetre
3. "°C" = Celsius degree
4. MDL= Method Detection Limit
5. ND = Not Detected, less than MDL
6. The specification was quoted from Council of Europe Resolution AP (2004)5.

2. Specific Migration of Bisphenol A*

Test Item	Result (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.1		
Migration of Bisphenol A	ND	0.01	0.05

Note:

1. Test Method: With reference to CEN/TS 13130-13-2005, sample preparation in 3% acetic acid at 70°C for 2 hours, analysis was performed by GC-MS.
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from regulation (EU) No 10/2011.
6. The testing item marked with "*" does not been accredited by CNAS.

3. Extractable Lead and Cadmium Content

Test Items	Result (mg/L)	MDL (mg/L)	Limit (mg/L)
	No.2		
Extractable Lead	ND	0.1	4.0
Extractable Cadmium	ND	0.01	0.3

Note:

1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-OES.
2. "mg/L" = milligram per litre
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from 84/500/EC (2005/31/EC).





Sample Photo:







Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Red silicone rubber	Silicone rubber
2		White ceramic	Ceramic

===== End of Report =====

WALTEK