



中国认可
国际互认
检测
TESTING
CNAS L6478



TEST REPORT

Reference No. : WTF18F10127637C

Applicant : Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

Manufacturer : 115253

Sample Name : Stainless steel mug, Double wall travel cup

Model No. : MO3559, MO9618

Test Requested : In accordance with Regulation (EU) No 10/2011 with amendments (EU) 2016/1416, (EU) 2017/752, (EU)2018/79, (EU)2018/213, Regulation (EC) No 1935/2004 and Council of Europe Resolution CM/Res(2013)9.

Test Conclusion : **Pass** (Please refer to next pages for details)

Date of Receipt sample : 2018-10-30

Date of Test : 2018-10-30 to 2018-11-07

Date of Issue : 2018-11-07

Test Result : Please refer to next page(s)

Remark : Selected test(s) as requested by applicant

Remarks:

The results shown in this test report refer only to the sample(s) tested, this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

Prepared By:

Waltek Services (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

Abby. Zhou

Abby. Zhou / Project Engineer

Approved by:



Dino Zhang

Dino Zhang / Lab Manager

**Test Results:****1. Overall Migration Test**

Food Simulant	Test Condition	Result (mg/dm ²)		MDL (mg/dm ²)	Limit (mg/dm ²)
		No.1	No.2		
3% Acetic Acid	70°C for 2 hours	ND	ND	3	10
50% Ethanol	70°C for 2 hours	ND	ND	3	10

Note:

1. Test method: With reference to BS EN 1186-1: 2002, BS EN 1186-3: 2002, BS EN 1186-9: 2002 and BS EN1186-14: 2002.
2. "mg/dm²" = milligram per square decimetre
3. "°C" = Celsius degree
4. MDL= Method Detection Limit
5. ND = Not Detected, less than MDL
6. The specification was quoted from (EU) No 10/2011 and its amendments (EU) 2016/1416 and (EU) 2017/752.

Food Simulant	Test Condition	Result (mg/kg)	MDL(mg/kg)	Limit (mg/kg)
		No.3		
3% Acetic Acid	70°C for 2 hours	ND	20	60
50% Ethanol	70°C for 2 hours	ND	20	60

Note:

1. Test method: With reference to BS EN 1186-1: 2002, BS EN 1186-3: 2002, BS EN 1186-9: 2002 and BS EN1186-14: 2002.
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. "°C" = Celsius degree
4. MDL= Method Detection Limit
5. ND = Not Detected, less than MDL
6. The specification was quoted from Council of Europe Resolution AP (2004)5.

**2. Specific Migration of heavy metal (Nickel, Aluminium, Barium, Cobalt, Copper, Iron, Lithium, Manganese, Zinc)**

Test Items	Result (mg/kg)		MDL (mg/kg)	Limit (mg/kg)
	No.1	No.2		
Specific migration of Nickel	ND	ND	0.01	0.02
Specific migration of Aluminium	ND	ND	0.1	1
Specific migration of Barium	ND	ND	0.1	1
Specific migration of Cobalt	ND	ND	0.01	0.05
Specific migration of Copper	ND	ND	0.1	5
Specific migration of Iron	ND	ND	0.1	48
Specific migration of Lithium	ND	ND	0.01	0.6
Specific migration of Manganese	ND	ND	0.01	0.6
Specific migration of Zinc	ND	ND	0.1	5

Note:

1. Test Method: With reference to BS EN 13130-1: 2004, sample preparation in 3% acetic acid at 70°C for 2 hours, analysis was performed by ICP-OES.
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from (EU) No 10/2011 and its amendments (EU) 2016/1416 and (EU) 2017/752.

3. Specific Migration of Acrylonitrile

Test Item	Result (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.1		
Migration of Acrylonitrile	ND	0.01	Not Detected (<0.01mg/kg)

Note:

1. Test Method: With reference to BS EN 13130-3: 2004, sample preparation in 3% acetic acid at 70°C for 2 hours, analysis was performed by HS-GC-MS.
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from (EU) No 10/2011.

**4. Council of Europe Resolution CM/Res(2013)9-Specific Migration of Heavy Metal**

Test Items	1st+2nd Migration (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.4		
Aluminium (Al)	ND	0.2	35
Antimony (Sb)	ND	0.02	0.28
Chromium (Cr)	ND	0.04	1.75
Cobalt (Co)	ND	0.02	0.14
Copper (Cu)	ND	0.2	28
Iron (Fe)	1.0	0.4	280
Manganese (Mn)	ND	0.2	12.6
Molybdenum (Mo)	ND	0.02	0.84
Nickel (Ni)	0.02	0.02	0.98
Silver (Ag)	ND	0.02	0.56
Tin (Sn)	ND	0.2	700
Vanadium (V)	ND	0.01	0.07
Zinc (Zn)	ND	0.2	35
Arsenic (As)	ND	0.002	0.014
Barium (Ba)	ND	0.2	8.4
Beryllium (Be)	ND	0.01	0.07
Cadmium (Cd)	ND	0.002	0.035
Lead (Pb)	ND	0.01	0.07
Lithium (Li)	ND	0.01	0.336
Mercury (Hg)	ND	0.002	0.021
Thallium (Tl)	ND	0.0002	0.0007
Magnesium (Mg)	ND	0.2	--
Titanium (Ti)	ND	0.02	--



Test Items	3rd Migration (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.4		
Aluminium (Al)	ND	0.1	5
Antimony (Sb)	ND	0.01	0.04
Chromium (Cr)	ND	0.02	0.25
Cobalt (Co)	ND	0.01	0.02
Copper (Cu)	ND	0.1	4
Iron (Fe)	ND	0.2	40
Manganese (Mn)	ND	0.1	1.8
Molybdenum (Mo)	ND	0.01	0.12
Nickel (Ni)	ND	0.01	0.14
Silver (Ag)	ND	0.01	0.08
Tin (Sn)	ND	0.1	100
Vanadium (V)	ND	0.005	0.01
Zinc (Zn)	ND	0.1	5
Arsenic (As)	ND	0.001	0.002
Barium (Ba)	ND	0.1	1.2
Beryllium (Be)	ND	0.005	0.01
Cadmium (Cd)	ND	0.001	0.005
Lead (Pb)	ND	0.005	0.01
Lithium (Li)	ND	0.005	0.048
Mercury (Hg)	ND	0.001	0.003
Thallium (Tl)	ND	0.0001	0.0001
Magnesium (Mg)	ND	0.1	--
Titanium (Ti)	ND	0.01	--

Note:

1. Test Method: With reference to BS EN 13130-1: 2004, analysis was performed by ICP-OES and ICP-MS.
2. Test Condition and simulant: Sample(s) were migrated with 5g/L citric acid at 70°C for 2 hours.
3. "mg/kg" = milligram per kilogram of foodstuff in contact with
4. MDL = Method Detection Limit
5. ND = Not Detected, less than MDL
6. "--" = Not regulated
7. The specification was quoted from Technical Guide on Metals and alloys used in food contact materials of Council of Europe Resolution CM/Res(2013)9.







Sample Photo:





Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Red plastic	ABS
2		Red plastic	PP
3		Translucent silicone rubber	Silicone rubber
4		Silvery metal	Stainless steel

===== End of Report =====