



中国认可
国际互认
检测
TESTING
CNAS L6478



TEST REPORT

Reference No. : WTF18F10127618X1C

Applicant : Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

Manufacturer : 107561

Sample Name : Espresso cup and saucer

Model No. : MO9634

Test Requested : In accordance with Council of Europe Resolution 84/500/EC (2005/31/EC) and Regulation (EC) No 1935/2004.

Test Conclusion : **Pass** (Please refer to next pages for details)

Date of Receipt sample : 2018-10-30

Date of Test : 2018-10-30 to 2018-11-07

Date of Issue : 2018-11-07

Test Result : Please refer to next page (s)

Remark : This report is based on Waltek test report WTF18F10127618C for revising, and replaced report WTF18F10127618C.

Remarks:

The results shown in this test report refer only to the sample(s) tested, this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

Prepared By:

Waltek Services (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

Abby Zhou

Abby.Zhou / Project Engineer

Approved by:



Dino Zhang

Dino.Zhang / Lab Manager



Test Results:


Test Items	Result (mg/L)	MDL (mg/L)	Limit (mg/L)
	No.1		
Extractable Lead	ND	0.1	4.0
Extractable Cadmium	ND	0.01	0.3

Test Items	Result (mg/dm ²)	MDL (mg/dm ²)	Limit (mg/dm ²)
	No.2		
Extractable Lead	ND	0.1	0.8
Extractable Cadmium	ND	0.01	0.07

Note:



1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-OES.
2. "mg/L" = milligram per litre
3. "mg/dm²" = milligram per square decimetre
4. MDL= Method Detection Limit
5. ND = Not Detected, less than MDL
6. The specification was quoted from 84/500/EC (2005/31/EC).

Sample Photo:





Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
1		White ceramic	Ceramic
2		White ceramic	Ceramic

===== End of Report =====

WALTEK