



中国认可  
国际互认  
检测  
TESTING  
CNAS L6478



# TEST REPORT

**Reference No.** ..... : WTF19F05028782C

**Applicant** ..... : Mid Ocean Brands B.V.

**Address** ..... : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

**Manufacturer** ..... : 111025

**Sample Name** ..... : Champagne glasses, glass cups w/coasters, double wall glass w/ lid

**Model No.** ..... : CX1465, MO9709, MO9719, MO9720, MO9721

**Test Requested** ..... : In accordance with Regulation (EU) No 10/2011, Council of Europe Resolution 84/500/EC (2005/31/EC), Council of Europe Resolution AP(2004)5 and Regulation (EC) No 1935/2004.

**Test Conclusion** ..... : **Pass** (Please refer to next pages for details)

**Date of Receipt sample** .... : 2019-05-08

**Date of Test** ..... : 2019-05-08 to 2019-05-20

**Date of Issue** ..... : 2019-05-20

**Test Result** ..... : Please refer to next page (s)

**Remarks:**

The results shown in this test report refer only to the sample(s) tested, this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

**Prepared By:**

**Waltek Services (Foshan) Co., Ltd.**

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

*Abby.Zhou*

Abby.Zhou / Project Engineer

Approved by:



*Ding Zhang*  
Ding Zhang / Lab Manager

**Test Results:****1. Extractable Lead and Cadmium Content**

Test Items	Result (mg/L)		MDL (mg/L)	Limit (mg/L)
	No.1	No.2		
Extractable Lead	ND	ND	0.1	4.0
Extractable Cadmium	ND	ND	0.01	0.3

## Note:

1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-OES.
2. "mg/L" = milligram per litre
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from 84/500/EC (2005/31/EC).

**2. Specific Migration of Formaldehyde\***

Test Item	Result (mg/dm <sup>2</sup> )	MDL (mg/dm <sup>2</sup> )	Limit (mg/dm <sup>2</sup> )
	No.3		
Migration of Formaldehyde	ND	0.1	1.0

## Note:

1. Test Method: With reference to BS EN 13130-1: 2004, sample preparation in 3% acetic acid at 40°C for 2 hours, analysis was performed by UV-visible Spectrometer.
2. "mg/dm<sup>2</sup>" = milligram per square decimetre
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from regulation (EU) No 10/2011.
6. The testing item marked with "\*" does not been accredited by CNAS.

**3. Pentachlorophenol (PCP) Content\***

Test Item	Result (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.3		
Pentachlorophenol (PCP)	ND	0.10	0.15

## Note:

1. Test method: With reference to LFGB § 64 BVL B 82.02.8-2001, analysis was performed by GC-MS.
2. "mg/kg" = milligram per kilogram
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from Council of Europe Resolution AP(2002)1.
6. The testing item marked with "\*" does not been accredited by CNAS.

**4. Overall Migration Test**

Food Simulant	Test Condition	Result (mg/kg)	MDL(mg/kg)	Limit (mg/kg)
		No.4		
3% Acetic Acid	40°C for 2 hours	ND	20	60
50% Ethanol	40°C for 2 hours	ND	20	60

Note:

1. Test method: With reference to BS EN 1186-1: 2002, BS EN 1186-3: 2002, BS EN 1186-9: 2002 and BS EN1186-14: 2002.
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. "°C" = Celsius degree
4. MDL= Method Detection Limit
5. ND = Not Detected, less than MDL
6. The specification was quoted from Council of Europe Resolution AP (2004)5.

**5. Bisphenol A Content\***

Test Item	Result (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.4		
Bisphenol A	ND	0.1	Not Detected (<0.1mg/kg)

Note:

1. Test Method: With reference to EPA3550C:2007, analysis was performed by LC-MS/MS.
2. "mg/kg" = milligram per kilogram
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from regulation (EU) No 10/2011.
6. The testing item marked with '\*' does not been accredited by CNAS.






**Sample Photo:**



**Photograph of parts tested:**

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Transparent glass	Glass



No.	Photo of testing part	Parts Description	Client Claimed Material
2		Transparent glass	Glass
3		Wood	Wood
4		Translucent silicone rubber	Silicone rubber

===== End of Report =====