



中国认可
国际互认
检测
TESTING
CNAS L6478



TEST REPORT

Reference No. : WTF19F04020295A5C

Applicant : Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

Manufacturer : 111999

Sample Name : Mug

Model No. : MO9708

Test Requested : In accordance with Council of Europe Resolution 84/500/EC (2005/31/EC), Resolution AP(2002)1 and Regulation (EC) No 1935/2004

Test Conclusion : **Pass** (Please refer to next pages for details)

Date of Receipt sample : 2019-04-12 & 2019-04-26 & 2019-05-21 & 2019-05-27 & 2019-06-03

Date of Test : 2019-04-12 to 2019-06-13

Date of Issue : 2019-06-13

Test Result : Please refer to next page (s)

Remark : Selected test(s) as requested by applicant.

Remarks:

The results shown in this test report refer only to the sample(s) tested, this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

Prepared By:

Waltek Services (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

Abby.Zhou

Abby.Zhou / Project Engineer

Approved by:



Ding Zhang

Ding Zhang / Lab Manager

**Test Results:****1. Extractable Lead and Cadmium Content**

Test Items	Result (mg/L)	MDL (mg/L)	Limit (mg/L)
	No.1		
Extractable Lead	ND	0.1	4.0
Extractable Cadmium	ND	0.01	0.3

Test Items	Result (mg/dm ²)	MDL (mg/dm ²)	Limit (mg/dm ²)
	No.2		
Extractable Lead	ND	0.1	0.8
Extractable Cadmium	ND	0.01	0.07

Note:

1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-OES.
2. "mg/L" = milligram per litre
3. "mg/dm²" = milligram per square decimetre
4. MDL= Method Detection Limit
5. ND = Not Detected, less than MDL
6. The specification was quoted from 84/500/EC (2005/31/EC).

2. Pentachlorophenol (PCP) Content*

Test Item	Result (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.3		
Pentachlorophenol (PCP)	ND	0.10	0.15

Note:

1. Test method: With reference to LFGB § 64 BVL B 82.02.8-2001, analysis was performed by GC-MS.
2. "mg/kg" = milligram per kilogram
3. MDL= Method Detection Limit
4. ND = Not Detected, less than MDL
5. The specification was quoted from Council of Europe Resolution AP(2002)1.
6. The testing item marked with '*' does not been accredited by CNAS.



3. Specific Migration of Formaldehyde*

Test Item	Result (mg/dm ²)	MDL (mg/dm ²)	Limit (mg/dm ²)
	No.3		
Migration of Formaldehyde	0.1	0.1	1.0

Note:




1. Test Method: With reference to EN 13130-1: 2004, sample preparation in 3% acetic acid at 40°C for 0.5 hour, analysis was performed by UV-visible Spectrometer.
2. "mg/dm²" = milligram per square decimetre
3. MDL= Method Detection Limit
4. The specification was quoted from regulation (EU) No 10/2011.
5. The testing item marked with '*' does not been accredited by CNAS

Sample Photo:





Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
1		White ceramic	Ceramic
2		White ceramic	Ceramic
3		Wood	Wood

==== End of Report =====