



TEST REPORT

Test Report # 19A-005717-2 Date of Report Issue: September 26, 2019
 Date of Sample Received: September 24, 2019 Pages: Page 1 of 10

CLIENT INFORMATION:

Company: Mid Ocean Brands B.V.
 Address: 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong



SAMPLE INFORMATION:

Product Name: Small waterproof bag
 Style No.: - Labeled Age Grade: -
 Order No.(PO No.): - Client Request Age Grade: -
 Country of Origin: - Recommended Age Grade: -
 Country of Distribution: - Tested Age Grade: -
 Model No.: MO8788
 Composition/Main Material: PVC,POM
 Buyer Name: Mid Ocean Brands B.V.
 Supplier Name: 100396
 Testing Period: 09/24/2019-09/26/2019

OVERALL RESULT:

PASS

Please refer to the following pages for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD

August Yuan
Operation Manager

Kevin Lee
Technical Manager



HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158
5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainspection Testing Technology Co., Ltd



TEST REPORT

Test Report # 19A-005717-2 Date of Report Issue: September 26, 2019
Date of Sample Received: September 24, 2019 Pages: Page 2 of 10

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 63 Lead in Substrate Materials
PASS	Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 23 Cadmium in Substrate Materials
PASS	Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 43 Azocolorants in Textiles
PASS	Regulation (EC) No. 1907/2006 REACH Annex XVII as amended, Item 51 and 52 Phthalates – Mouthable (DBP, BBP, DEHP, DIBP, DnOP, DINP, DIDP)
PASS	Colour Fastness to Rubbing

Remark: Test results are transferred from test report no. 19A-005717-1 date: 09/26/2019



HANGZHOU ASIAINPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158
5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China

*The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainpection Testing Technology Co., Ltd*



DETAILED RESULTS:

Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 63 Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal) and/or CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	5	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	7	8	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	---	---	500
Conclusion	PASS	PASS	PASS	---	---	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)





DETAILED RESULTS:

Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 23 Cadmium in Substrate Materials

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	5	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Cadmium (Cd)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	7	8	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Cadmium (Cd)	ND	ND	ND	---	---	100
Conclusion	PASS	PASS	PASS	---	---	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15mg/kg)




**DETAILED RESULTS:****Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 43 Azocolorants in Textiles**

Test Method: EN 14362-1:2012

Analytical Method: Gas Chromatography with Mass Spectrometry/ Liquid Chromatography-Mass Spectrometer (LC-MS)

Specimen No.		1	6	---	---	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
4-aminobiphenyl	92-67-1	ND	ND	---	---	30
Benidine	92-87-5	ND	ND	---	---	30
4-chloro-o-toluidine	95-69-2	ND	ND	---	---	30
2-naphtylamine	91-59-8	ND	ND	---	---	30
2-Amino-4-Nitrotoluene	97-56-3	ND	ND	---	---	30
5-nitro-o-toluidine	99-55-8	ND	ND	---	---	30
4-chloroaniline	106-47-8	ND	ND	---	---	30
4 methoxy-m -phenylenediamine	615-05-4	ND	ND	---	---	30
4,4'-diaminodiphenyl methane	101-77-9	ND	ND	---	---	30
3,3'-dichlorobenzidine	91-94-1	ND	ND	---	---	30
3,3'-dimethoxybenzidine	119-90-4	ND	ND	---	---	30
3,3'-dimethylbenzidine	119-93-7	ND	ND	---	---	30
3,3'-dimethyl-4,4'-diaminodiphenyl methane	838-88-0	ND	ND	---	---	30
p-cresidine	120-71-8	ND	ND	---	---	30
4,4'-methylene-bis-(2-chloro-aniline)	101-14-4	ND	ND	---	---	30
4,4'-oxydianiline	101-80-4	ND	ND	---	---	30
4,4'-thiodianiline	139-65-1	ND	ND	---	---	30
o-toluidine	95-53-4	ND	ND	---	---	30
2,4-toluylenediamine	95-80-7	ND	ND	---	---	30
2,4,5-trimethylaniline	137-17-7	ND	ND	---	---	30
2-methoxyaniline	90-04-0	ND	ND	---	---	30
4-aminoazobenzene	60-09-3	ND	ND	---	---	30
Conclusion		PASS	PASS	---	---	



HANGZHOU ASIAINPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158
5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainpection Testing Technology Co., Ltd



Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 5 mg/kg)

Remark:

In the case of levels per amine component less than or equal to 30 mg/kg, according to the analysis as carried out, azo colorants which can release one or more of certain listed amines by cleavage of their azo group/s were not detected in the commodity submitted.



**DETAILED RESULTS:****Regulation (EC) No. 1907/2006 REACH Annex XVII as amended, Item 51 and 52 Phthalates – Mouthable (DBP, BBP, DEHP, DIBP, DnOP, DINP, DIDP)**

Test Method: CPSC-CH-C1001-09.4

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	7	8	Limit (mg/kg)
Test Item	CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	1000
Sum of DBP, BBP, DEHP, DIBP		ND	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	
Sum of DnOP, DINP, DIDP		ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 150 mg/kg)





DETAILED RESULTS:

Colour Fastness to Rubbing

Test Method: ISO 105-X12: 2016, Size of rubbing finger: 16mm dia.

Specimen No.	1	---	---	---	---	Client's requirement
Items	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	Result (Grade)	
Dry staining	4-5	---	---	---	---	Min. 2-3
Wet staining	4-5	---	---	---	---	Min. 2-3
Conclusion	PASS	---	---	---	---	-

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.





SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Blue coated blue textile	Main body(blue style)
2	White coated white textile	Main body(white style)
3	Yellow coated yellow textile	Main body(yellow style)
4	Red coated red textile	Main body(red style)
5	Black coated black textile	Main body(black style)
6	Black textile	Cord(blue style)
7	Black plastic	Buckle pin(blue style)
8	Transparent soft plastic	Centre joint(blue style)





SAMPLE PHOTO:



-End Report-

