



TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 1 of 14

Client : Mid Ocean Brands B.V.

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

The following merchandise was (were) submitted and identified by the client as:

Name of Product : Double wall vacuum bottle with bamboo body.

Test Model : MO9991

Model May Cover : /

Main Material: /

Supplier: 107961

Buyer: /

Sample Received : Oct. 28, 2019

Test Period : Oct. 28, 2019 - Oct. 31, 2019

Test Specification and Conclusion:

Please refer to next page

Prepared By :

David Chen
Testing Engineer

Reviewed By :

Dora Cheng
Reporter Supervisor

Issued By :



Ada Wang
Lab Manager



SZ2019100885-1E

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com



TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 2 of 14

Test Request	Conclusion
Technical Guide on Metals and Alloys used in food contact materials and articles of the 1 st edition in 2013, General Requirement(Article 3) in EU Regulation No. 1935/2004	
1. Extractable Heavy Metals for metal	PASS
Commission Regulation (EU) No 10/2011 and its subsequent amendment Regulation EU No.1282/2011, 1183/2012, 202/2014 and Regulation (EU) 2016/1416, (EU) 2017/752, (EU) 2018/213 on plastic materials and articles intended to come into contact with foodstuffs, General Requirement(Article 3) in EU Regulation No. 1935/2004	
2. Overall Migration test for plastic	PASS
3. Soluble Heavy Metals for plastic	PASS
4. Specific Migration of Bisphenol-A for plastic	PASS
5. Specific Migration of acrylonitrile for plastic	PASS
6. Specific Migration of 1,3-butadiene for plastic	PASS
European Commission Directive 1935/2004/EC relating to materials and articles intended to come into contact with foodstuffs	
7. Specific Migration of Melamine for wood	PASS
8. Lead (Pb) content according to EC Regulation 1907/2006, REACH Annex XVII (entry 63)	PASS
9. Cadmium (Cd) content according to EC Regulation 1907/2006, REACH Annex XVII (entry 23)	PASS
10. Phthalate content according to EC Regulation 1907/2006, REACH Annex XVII (entry 51&52)	PASS
11. Polycyclic Aromatic Hydrocarbons (PAHs) contents according to AfPS GS 2014:01 PAK	PASS
12. Formaldehyde content according to Safety of Toys, EN71-9:2005+ A1:2007-Organic Chemical Compounds	PASS

***** To be continued *****

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 3 of 14

TEST RESULTS:

1.Extractable Heavy Metals

Test Method: Sample prepared with reference to Technical Guide on Metals and Alloys used in food contact materials and articles of the 1st edition in 2013 and by ICP-OES & ICP-MS

Test condition: 100°C, 1 hour with Citric acid (5 g/L)

Test sample No and description: 1# Silver metal inner wall

Extractable Elements	The 1 st Result (mg/kg)	The 2 nd Result (mg/kg)	The 1 st + 2 nd Result (mg/kg)	7*Limit (mg/kg)	The 3rd Result (mg/kg)	Limit (mg/kg)
Silver (Ag)	N.D.	N.D.	N.D.	0.56	N.D.	0.08
Aluminium (Al)	N.D.	N.D.	N.D.	35	N.D.	5
Chromium (Cr)	N.D.	N.D.	N.D.	1.75	N.D.	0.250
Cobalt (Co)	N.D.	N.D.	N.D.	0.14	N.D.	0.02
Copper (Cu)	N.D.	N.D.	N.D.	28	N.D.	4
Iron (Fe)	0.12	0.04	0.16	280	0.02	40
Magnesium (Mg)	0.01	N.D.	0.01	---	N.D.	---
Manganese (Mn)	N.D.	N.D.	N.D.	12.6	N.D.	1.8
Molybdenum (Mo)	N.D.	N.D.	N.D.	0.84	N.D.	0.12
Nickel (Ni)	0.04	N.D.	0.04	0.98	N.D.	0.14
Tin (Sn)	N.D.	N.D.	N.D.	700	N.D.	100
Titanium (Ti)	N.D.	N.D.	N.D.	---	N.D.	---
Vanadium (V)	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Zinc (Zn)	0.02	N.D.	0.02	35	N.D.	5
Antimony (Sb)	N.D.	N.D.	N.D.	0.28	N.D.	0.04
Arsenic (As)	N.D.	N.D.	N.D.	0.014	N.D.	0.002
Barium (Ba)	N.D.	N.D.	N.D.	8.4	N.D.	1.2
Beryllium (Be)	N.D.	N.D.	N.D.	0.07	N.D.	0.01
Cadmium (Cd)	N.D.	N.D.	N.D.	0.035	N.D.	0.005
Lead (Pb)	N.D.	N.D.	N.D.	0.07	N.D.	0.010
Lithium (Li)	N.D.	N.D.	N.D.	0.336	N.D.	0.048
Mercury (Hg)	N.D.	N.D.	N.D.	0.021	N.D.	0.003
Thallium (Tl)	N.D.	N.D.	N.D.	0.0007	N.D.	0.0001

***** To be continued *****

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.:+86/(0)512 67991866

Fax: +86/(0)512 87661802

Web:www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 4 of 14

Remark:

1. The following table is the MDL of the Extractable Heavy Metals testing

Extractable Elements	MDL(mg/kg)	Extractable Elements	MDL(mg/kg)	Extractable Elements	MDL(mg/kg)
Silver (Ag)	0.01	Molybdenum (Mo)	0.01	Barium (Ba)	0.01
Aluminium (Al)	0.01	Nickel (Ni)	0.01	Beryllium (Be)	0.01
Chromium (Cr)	0.01	Tin (Sn)	0.01	Cadmium (Cd)	0.001
Cobalt (Co)	0.01	Titanium (Ti)	0.01	Lead (Pb)	0.001
Copper (Cu)	0.01	Vanadium (V)	0.01	Lithium (Li)	0.01
Iron (Fe)	0.01	Zinc (Zn)	0.01	Mercury (Hg)	0.001
Magnesium (Mg)	0.01	Antimony (Sb)	0.01	Thallium (Tl)	0.0001
Manganese (Mn)	0.01	Arsenic (As)	0.001	---	---

2. MDL = Method Detection Limit.

3. N.D.= Not detected, less than MDL.

4. The submitted sample/component is a repeated use article. The migration test was carried out three times on the same article. The sum of the results of the first and second tests should not exceed seven times the limit (Result 1st test + Result 2nd test <7* limit) and the Result 3rd should not exceed the limit.

2.Overall Migration Test

Test Method: With reference to EN1186-1:2002 for selection of conditions and test methods;
EN1186-3:2002 aqueous food simulants by total immersion method;

Surface area(dm²)/Volume(ml):

2# 1/100

3# 1/100

Simulant Used	Unit	Test Condition	Result		Maximum Permissible Limit
			2#	3#	
3% Acetic Acid (W/V) Aqueous Solution	mg/dm ²	1 hour at 100°C	<3.0	<3.0	10
50% Ethanol (V/V) Aqueous Solution	mg/dm ²	1 hour at 100°C	<3.0	<3.0	10

Remark: Report the third extractive results.

***** To be continued *****

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 5 of 14

3.Soluble Heavy Metals

Test Method: Sample preparation in 3% Acetic acid at 100°C for 1 hour, followed by analysis using Inductively Coupled Argon Plasma Spectrometer.

Surface area(dm²)/Volume(ml):

2# 1/167

3# 1/167

Test Item	Unit	Result		Maximum Permissible Limit
		2#	3#	
Soluble Barium	mg/kg	<0.01	<0.01	1
Soluble Cobalt	mg/kg	<0.01	<0.01	0.05
Soluble Copper	mg/kg	<0.01	<0.01	5
Soluble Iron	mg/kg	0.03	<0.01	48
Soluble Lithium	mg/kg	<0.01	<0.01	0.6
Soluble Manganese	mg/kg	<0.01	<0.01	0.6
Soluble Zinc	mg/kg	<0.01	<0.01	5
Soluble Aluminum	mg/kg	0.02	<0.01	1
Soluble Nickel	mg/kg	<0.01	<0.01	0.02

Remark: Report the third extractive results.

4.Specific Migration of Bisphenol-A

Test Method: Sample preparation with reference to BS EN 13130-1:2004 with selection of simulants and condition, followed by analysis using High Performance Liquid Chromatography/ Mass Spectrometer (HPLC/MS).

Surface area(dm²)/Volume(ml):

2# 1/167

3# 1/167

Test Items	Unit	Result		Maximum Permissible Limit
		2#	3#	
Specific migration of Bisphenol-A in 3% acetic acid at 100°C,1 hour	mg/kg	<0.01	<0.01	0.05

Remark: Report the third extractive results.

***** To be continued *****

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 6 of 14

5. Specific Migration of Acrylonitrile

Test Method: Sample preparation with reference to EN 13130-1: 2004 with selection of simulant and condition, followed by analysis by HS-GC/MS.

Surface area(dm²)/Volume(ml): 1/167

Test Items	Unit	Result	Maximum Permissible Limit
		3#	
Specific Migration of acrylonitrile in 3% acetic acid at 100°C, 1 hour	mg/kg	<0.01	0.01

6. Specific Migration of 1,3-butadiene

Test Method: Sample preparation with reference to EN 13130-1: 2004 with selection of simulant and condition, followed by analysis by HS-GC/MS.

Surface area(dm²)/Volume(ml): 1/167

Test Items	Unit	Result	Maximum Permissible Limit
		3#	
Specific Migration of 1,3-butadiene in 3% acetic acid at 100°C, 1 hour	mg/kg	<0.01	0.01

7. Specific Migration of Melamine

Test Method: Sample preparation with reference to BS EN 13130-1:2004 with selection of simulants and condition, followed by analysis using High Performance Liquid Chromatography / Mass Spectrometer (HPLC/MS).

Surface area(dm²)/Volume(ml): 1/167

Test Items	Unit	Result	Maximum Permissible Limit
		4#	
Specific migration of Melamine in 3% acetic acid at 100°C, 1 hour	mg/kg	< 0.1	2.5

Remark: Report the third extractive results.

8. Lead(Pb) Content

Test Method: With reference to EPA 3050B-1996 & EPA 6010D-2018, Analysis was performed by ICP-AES.

Test Item	MDL (mg/kg)	Test Results (mg/kg)	Limited Value* (mg/kg)
		1#	
Lead(Pb)	10	N.D.	500

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com



TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 7 of 14

Test Method: With reference to EPA 3052-1996 & EPA 6010D-2018, Analysis was performed by ICP-AES.

Test Item	MDL (mg/kg)	Test Results (mg/kg)			Limited Value* (mg/kg)
		2#	3#	4#	
Lead(Pb)	10	N.D.	N.D.	N.D.	500

Remark: *The Limited value is based on EC Regulation 1907/2006, REACH Annex XVII (entry 63).

9.Cadmium (Cd) Content

Test Method: With reference to EN 1122- 2001 Method B, Analysis was performed by ICP-AES.

Test Item(s)	MDL (mg/kg)	Test Results (mg/kg)			Limited Value** (mg/kg)
		2#	3#	4#	
Cadmium (Cd)	10	N.D.	N.D.	N.D.	100

Remark: **The Limited value is based on EC Regulation 1907/2006, REACH Annex XVII (entry 23).

***** To be continued *****

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 8 of 14

10. Phthalates Content

Test Method: With reference to EN 14372-2004, Analysis was performed by GC-MS.

(11-1) For plasticized materials (including toys and childcare articles)

Test Item(s)	Unit	MDL	Test Results		Limited Value***
			2#	3#	
Dibutyl Phthalate((DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate(BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate(DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	< 0.1

(11-2) For toys and childcare articles that can be mouthed

Test Item(s)	Unit	MDL	Test Results		Limited Value***
			2#	3#	
Di-iso-nonylphthalate(DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate(DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate(DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	< 0.1

Remark: ***The Limited value is based on EC Regulation 1907/2006, REACH Annex XVII (entry 51&52).

***** To be continued *****

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 9 of 14

11.PAHs Contents

Test Method: With reference to AfPS GS 2014:01 PAK, Analysis was performed by GC-MS.

Test Items	Unit	MDL	Test Results	
			2#	3#
Naphthalene	mg/kg	0.1	N.D.	N.D.
Acenaphthylene		0.1	N.D.	N.D.
Acenaphthene		0.1	N.D.	N.D.
Fluorene		0.1	N.D.	N.D.
Phenanthrene		0.1	N.D.	N.D.
Anthracene		0.1	N.D.	N.D.
Fluoranthene		0.1	N.D.	N.D.
Pyrene		0.1	N.D.	N.D.
Benzo[a]anthracene		0.1	N.D.	N.D.
Chrysene		0.1	N.D.	N.D.
Benzo[b]fluoranthene		0.1	N.D.	N.D.
Benzo[k]fluoranthene		0.1	N.D.	N.D.
Benzo[a]pyrene		0.1	N.D.	N.D.
Indeno[1,2,3-cd]pyrene		0.1	N.D.	N.D.
Dibenzo[a,h]anthracene		0.1	N.D.	N.D.
Benzo[g,h,i]perylene		0.1	N.D.	N.D.
Benzo[j]fluoranthene		0.1	N.D.	N.D.
Benzo[e]pyrene		0.1	N.D.	N.D.
Sum of 18 PAHs		---	N.D.	N.D.

***** To be continued *****

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 10 of 14

LIMITS(mg/kg) FOR PAH IN PRODUCTS:

Parameter	Category 1	Category2		Category 3	
		Toys by Directive 2009/48/EC	Other products by ProdSG	Toys by Directive 2009/48/EC	Other products by ProdSG
	To be taken materials which are intended in the mouth, or materials in toys intended and with long-term skin contact (longer than 30 seconds)	Materials that are not covered in Category 1, with predictable skin contact longer than 30 seconds (long-term skin contact) or repeated short-term skin contact		Materials that do not fall into Category 1 & Category 2, With predictable skin contact up to 30 s (short-term skin contact)	
Naphthalene	< 1	< 2		< 10	
Acenaphthylene	Total < 1	Total < 5	Total < 10	Total < 20	Total < 50
Acenaphthene					
Fluorene					
Phenanthrene					
Anthracene					
Fluoranthene					
Pyrene					
Benzo[a]anthracene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Chrysene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[b]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[k]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[a]pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Indeno[1,2,3-cd]pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Dibenzo[a,h]anthracene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[g,h,i]perylene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[j]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[e]pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Sum of 18 PAHs	< 1	< 5	< 10	< 20	< 50

***** To be continued *****

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 11 of 14

12. Formaldehyde content

Test Method: With reference to EN 717-3-1996, Analysis was performed by UV-Vis.

Test Item	Moisture content (%)	MDL (mg/kg)	Test Results (mg/kg)	Limited Value**** (mg/kg)
			4# ^Δ	
Formaldehyde	8.10	10	18	80

Remark: ****The Limited value is based on EN71-9:2005+A1:2007-Organic Chemical Compounds-Requirements

- Note :**
- 1) MDL = Method Detection Limit.
 - 2) N.D. = Not detected, less than MDL.
 - 3) “---” = Not Regulated.
 - 4) % = Percentage by weight.
 - 5) ^ΔThe test results are quoted from the results of sample 1# in SZ2019080976-1E.

Test Part Description:


1# Silver metal inner wall

2# Black PP


3# White ABS

4# Bamboo

SAMPLE PHOTOS



1#




2#

TEST REPORT


Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 12 of 14



3#



4#

***** END OF REPORT *****



TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 13 of 14

GENERAL CONDITIONS OF SERVICES

STQ Testing Services Co.,Ltd. (hereinafter "STQ"), while reserving the right to decline, without giving any reason whatsoever, any request for the undertaking of a test or investigation, will carry out at the request of the clients the required test or investigation subject always to the following conditions:

1. STQ only acts for the person or body originating the instructions (the "Clients"). No other party is entitled to give instructions, particularly on the scope of testing or delivery of report or certificate, unless authorized by the Clients.
2. The Sample(s) to be tested or investigated shall be delivered at the costs of the Clients and in accordance with the requirements of STQ. Improper shipping, packaging, and labeling of the Sample(s) by the Client may result in incorrect testing results, STQ shall be under no obligation to the Clients. At the conclusion of the test or investigation, the Clients shall, if required by STQ, collect the Sample(s). In any event, if the Sample(s) are not collected by the Clients within 60 days from the issuance date of the test report (for perishable items such as food and water samples, the relevant period shall be the preserving period up to 15 days), STQ may at its discretion dispose of the Sample(s) without any compensation to the Clients.
3. The Clients shall always comply with the following before or during STQ providing its services:
 - a) provide sample(s) and relevant data, at the same time, guarantee the consistence of the sample(s)' name they declared with the sample(s) or the goods provided. Otherwise, STQ will not bear any relevant responsibilities;
 - b) giving timely instructions and adequate information to enable STQ to perform the services effectively;
 - c) supply, when requested by STQ, any equipment and personnel for the performance of the services;
 - d) take all necessary steps to eliminate or remedy any obstruction in the performance of the services;
 - e) inform STQ in advance of any hazards or dangers, actual or potential, associated with any order of samples or testing;
 - f) provide all necessary access for STQ's representative to enable the required services to be performed effectively;
 - g) ensure all essential steps are taken for safety of working conditions, sites and installations during the performance of services;
 - h) fully discharge all its liabilities under any contract like sales contract with a third party, whether or not a report or certificate has been issued by STQ, failing which STQ shall be under no obligation to the Clients.
4. Subject to STQ's accepting the Client's instructions, STQ will issue reports or certificates which reflect statements of opinion made with due care within the scope of instructions but STQ is not obliged to report upon any facts outside the instructions, if there were any dissidence about the report or certificate, the Client should provide the written declaration to STQ within 15 days after the date receiving the report or certificate, otherwise, STQ will not hear the case after the date limit.
5. STQ is irrevocably authorized by the Clients to deliver at its discretion the report or the certificate to any third party when instructed by the Clients or where it implicitly follows from circumstances, trade custom, usage or practice as determined by STQ.
6. A test report will be issued in confidence to the Clients and it will be strictly treated as such by STQ. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of STQ. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by STQ, to his customer, supplier or other persons directly concerned. STQ will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the report unless required by the relevant governmental authorities, laws or court orders.
7. Applicants wishing to use STQ's reports in court proceedings or arbitration shall inform STQ to that effect prior to submitting the sample for testing.
8. The report will refer only to the sample tested and will not apply to the bulk, unless the sampling has been carried out by STQ and is stated as such in the Report. Also, the report is only for reference.
9. Any documents containing engagements between the Clients and third parties like contracts of sale, letters of credit, bills of lading, etc. are regarded as information for STQ only and do not affect the scope of the services or the obligations accepted by STQ.
10. If the Clients do not specify the methods/standards to be applied, STQ will choose the appropriate ones and further information regarding the methods can be obtained by direct contact with STQ, for the in-house method, STQ will only provide the summary.
11. No liability shall be incurred by and no claim shall be made against STQ or its servants, agents, employees or independent contractors in respect of any loss or damage to any such materials, equipment and property occurring whilst at STQ or any work places in which the testing is carried out, or in the course of transit to or from STQ or the said work places, whether or not resulting from any acts, neglect or default on the part of any such servants, agents, employees or independent contractors of STQ.
12. STQ will not be liable, or accept responsibility for any loss or damage howsoever arising from the use of information contained in any of its reports or in any communication whatsoever about its said tests or investigations.
13. Subject to Clause 11 and 12, the total liability of STQ in respect of any claim of loss, damage or expense of whatsoever nature shall not exceed a total sum equal to two times the amount of the service fee payable in respect of the services directly related to such claim, and STQ's liability shall not include any indirect, special or consequential loss of the Clients.
14. In the event of STQ prevented by any cause outside STQ's control from performing any service for which an order has been given or an agreement made, the Clients shall pay to STQ:
 - a) the amount of all abortive expenditure actually made or incurred;
 - b) a proportion of the agreed fee or commission equal to the proportion (if any) of the service actually carried out by STQ, and STQ shall be relieved of all responsibility whatsoever for the partial or total non-performance of the required service.
15. STQ shall be discharged from all liabilities for all claims for loss, damage or expense unless suit is brought within one calendar

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com



TEST REPORT

Reference No. : SZ2019100885-1E

Date : Nov. 01, 2019

Page No.: 14 of 14

year after the date of the performance by STQ of the service relating to the claim or in the event of any alleged non—performance within one year of the date when such service should have been completed.

- 16.The Clients acknowledge that STQ does not, either by entering into a contract or by performing service, assume or undertake to discharge any duty of the Clients to any other persons. STQ is neither an insurer nor a guarantor and disclaims all liability in such capacity.
- 17.The Clients shall hold harmless and indemnify STQ and its officers, employees, agents or independent contractors against all claims made by any third party for loss, damage or expense of whatsoever nature including reasonable legal expenses relating to the performance or non- performance of any services to the extent that the aggregate of any such claims relating to any one service exceed the limits mentioned in Clause 13.
- 18.Any unauthorized alteration, forgery or falsification of the content or appearance of the report/certificate is unlawful and offenders may be prosecuted to the fullest extent of the law; in the event of improper use of the report, STQ reserves the right to withdraw it, and to adopt any other measures which may be appropriate.
- 19.Samples are deposited with and accepted by STQ on the basis that either they are insured by the Clients or the Clients assumes entire responsibility for loss through fire, theft, burglary or for damages arising in the course of analysis or handling, without recourse whatsoever to STQ or its servants, agent, employees or independent contractors.
- 20.If the requirements of the Clients require the analysis of samples by the Clients' or any third party's laboratory, STQ will only convey the result of the analysis without responsibility for its accuracy. If STQ is only able to witness an analysis by the Clients' or any third Party's laboratory STQ will only confirm that the correct sample has been analyzed without responsibility for the accuracy of any analysis or results.
- 21.In the event of any unforeseen additional time or costs being incurred in the course of carrying out any of its services, STQ shall be entitled to charge the Clients additional fees to reflect the additional time and costs incurred.
- 22.All rights (including but not limited to copyright) in any reports, certificates or other materials produced by STQ in the course of providing its services shall remain vested in STQ.
- 23.Unless otherwise agreed in writing, payment is to be made within 10 days from the date of Invoice or the date of the Debit Note, all charges rendered by STQ or interest will become due at the rate of three percent per month from the date of invoice until actual payment. The Clients are also responsible for settling all STQ's costs of collecting the charges owed, including legal fees.
- 24.Test results may be transmitted by electronic means at the Client's request. However, it should be noted that electronic transmission cannot guarantee the information contained will not be lost, delayed or intercepted by third party. STQ is not liable for any disclosure, error or omission in the content of such messages as a result of electronic transmission.
- 25.If necessary, STQ may subcontract part of or all tests to competent subcontractors. If no objection is raised at the time of the Clients submitting the application, STQ shall assume the Client's approval.
- 26.This report/certificate does not relieve sellers/suppliers from their contractual responsibility with regards to the quality/quantity of this delivery nor does it prejudice the Client's right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during STQ's random inspection or testing or audit.
- 27.STQ reserves the right to include Special Conditions in addition to the foregoing General Conditions if warranted by the particular circumstances of the required test or investigation [this clause is only effective when the other party has been informed].
- 28.The foregoing General Conditions shall in all respects be governed, construed, interpreted and operated in accordance with the relevant Chinese laws and regulations. Unless otherwise agreed, the arbitration shall take place in P. R. C
- 29.These General Condition have been drafted in Chinese and may be translated into other languages. In the event of any discrepancy, the Chinese version shall prevail.
- 30.In general sample will be stored for 60 days. But for liquid, powder, etc semi-product & fragile product, it will be stored only for 7 days.
- 31.The effective date of this“GENERAL CONDITIONS OF SERVICES”is 1st May of 2017 and Version 2.0.

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.:+86/(0)512 67991866

Fax: +86/(0)512 87661802

Web:www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com