

中国认可 国际互认 检测 TESTING CNAS L6478



# **TEST REPORT**

Reference No.	:-11	WTF20F06037565F	
Applicant	:	Mid Ocean Brands B.V.	
Address	5)" : :[[]	7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong	
Manufacturer	:	109623	
Sample Name	ċ.	Ceramic mug	
Model No.	:	KC7062	
Test Requested	ini	In accordance with Council of Europe Resolution 84/500/EC (2005/31/EC) and Regulation (EC) No 1935/2004.	
Test Conclusion	MITE	Pass (Please refer to next pages for details)	
Date of Receipt sample	:	2020-06-16	
Date of Test	:	2020-06-16 to 2020-06-22	
Date of Issue	:	2020-06-22	
Test Result	:	Please refer to next page (s)	

#### Remarks:

The results shown in this test report refer only to the sample(s) tested; this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

## Prepared By: Waltek Services (Foshan) Co., Ltd. Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

by. Zhou

Abby.Zhou / Project Engineer

SERVICE Approved by: ng.Liang / Technical Manager STREPS

Waltek Services (Foshan) Co., Ltd. http://www.waltek.com.cn

Reference No.: WTF20F06037565F





Extractable Lead and Cadmium Content

Test Items	Result (mg/L)		Limit (mg/L)
	No.1	LOQ (mg/L)	
Extractable Lead	ND ND NO	0.1	4.0
Extractable Cadmium	ND ALL ND	0.01	0.3

Note:

1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-OES.

- 2. "mg/L" = milligram per litre
- 3. LOQ = Limit of quantitation
- 4. ND = Not Detected, less than limit of quantitation
- 5. The specification was quoted from 84/500/EC (2005/31/EC).

## Sample description:

No.1: White ceramic (Ceramic)

#### Sample Photo:



===== End of Report ======

Waltek Services (Foshan) Co., Ltd. http://www.waltek.com.cn