



# **TEST REPORT**

Reference No. ..... : WTF20F04016048F

Applicant .....: 1 Mid Ocean Brands B.V.

Address .....: 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon,

Hong Kong

Manufacturer .....: 114276

Sample Name .....: Tea box

Model No. ..... : MO9950

Test Requested.....: In accordance with Council of Europe Resolution AP(2002)1,

Regulation (EU) No 10/2011, Resolution 84/500/EC (2005/31/EC) and

Regulation (EC) No 1935/2004.

Test Conclusion...... : Pass (Please refer to next pages for details)

Date of Receipt sample .... : 2020-04-03

**Date of Test** : 2020-04-03 to 2020-04-17

**Date of Issue** ..... : 2020-04-17

Test Result .....: Please refer to next page (s)

#### Remarks:

The results shown in this test report refer only to the sample(s) tested; this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

### Prepared By: Waltek Services (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

Jessise Liu

Jessise.Liu / Project Engineer

Approved by:

Reference No.: WTF20F04016048F Page 2 of 4

#### **Test Results:**

1. Specific Migration of Formaldehyde\*

Test Item	Result (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.1	MDL (mg/kg)	
Migration of Formaldehyde	Furtil 6 Life wa	we 1 m	15

#### Note:

- 1. Test Method: With reference to BS EN 13130-1: 2004, sample preparation in 3% acetic acid at 40°C for 10 days, analysis was performed by UV-visible Spectrometer.
- 2. "mg/kg" = milligram per kilogram
- 3. MDL= Method Detection Limit
- 4. ND = Not Detected, less than MDL
- 5. The specification was quoted from regulation (EU) No 10/2011.
- 6. The testing item marked with '\*' does not been accredited by CNAS

2. Pentachlorophenol (PCP) Content\*

Test Item	Result (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.1		
Pentachlorophenol (PCP)	ND	0.10	0.15

#### Note:

- 1. Test method: With reference to LFGB § 64 BVL B 82.02.8-2001, analysis was performed by GC-MS.
- 2. "mg/kg" = milligram per kilogram
- 3. MDL= Method Detection Limit
- 4. ND = Not Detected, less than MDL
- 5. The specification was quoted from Council of Europe Resolution AP(2002)1.
- 6. The testing item marked with '\*' does not been accredited by CNAS

#### 3. Extractable Lead and Cadmium Content

nut whi d	Result (mg/dm²)	MDI (no gr/dino <sup>2</sup> )	1 : : ( ( 2 )
Test Items	No.2	MDL (mg/dm²)	Limit (mg/dm²)
Extractable Lead	THE THE NO THE WALLE OF	0.1	0.8
Extractable Cadmium	ND	0.01	0.07


#### Note:

- 1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-OES.
- 2. "mg/dm2" = milligram per square decimetre
- 3. MDL= Method Detection Limit
- 4. ND = Not Detected, less than MDL
- 5. The specification was quoted from 84/500/EC (2005/31/EC).



Reference No.: WTF20F04016048F Page 3 of 4

# **Sample Photo:**



## Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
WALTER		in whi whi w	I WHITEK WHITEK WHITE
1 -		Yellow wood	Wood
t write	5. 12, 5. 1. 10, pp. 115, pp. 120, pp. 125, pp. 130, pp. 135, pp. 10, pp. 15, pp. 120, pp. 125, pp. 130, pp. 135, pp. 10, pp. 15, pp. 120, pp. 125, pp. 130, pp. 135, pp. 10, pp. 15, pp. 120, pp. 125, pp. 130, pp. 135, pp. 140, pp. 15, pp. 140, pp.	nited whites whites	Write Murie Muries and



Reference No.: WTF20F04016048F

Page 4 of 4

No.	Photo of testing part	Parts Description	Client Claimed Material
	2, 5 - 7 - 7 10 p.p.p.15 n.p.n.20 n.p.n.25 n.p.n.20 n.p.n.35 n.p.n.00 n.	Transparent glass	Glass Military Market M

===== End of Report =====

