



TEST REPORT

Reference No.	WTF20F09067496A2F
Applicant	Mid Ocean Brands B.V.
Address	7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong
Manufacturer	106613
Sample Name	Bamboo cutting board
Model No.	MO6144
Test Requested	In accordance with Regulation (EU) No 10/2011, Council of Europe Resolution AP(2002)1, Council of Europe Resolution AP(2004)5 and Regulation (EC) No 1935/2004.
Test Conclusion	Pass (Please refer to next pages for details)
Date of Receipt sample	2020-09-17
Date of Test	2020-09-17 to 2020-09-25
Date of Issue	2020-10-28
Test Result	Please refer to next page (s)
Note	Selected test(s) as requested by applicant.

Remarks:

The results shown in this test report refer only to the sample(s) tested; this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

Prepared By:**Waltek Testing Group (Foshan) Co., Ltd.**

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City,

Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

Abby.Zhou

Abby.Zhou / Project Engineer

Approved by:

Dino Zhang

Dino Zhang / Authorized officer

**Test Results:****1. Specific Migration of Formaldehyde**

Test Item	Result (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
	No.1		
Migration of Formaldehyde	2	1	15

Note:

1. Test Method: With reference to BS EN 13130-1: 2004, sample preparation in 3% acetic acid at 70°C for 0.5 hour, analysis was performed by UV-visible Spectrometer.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. The specification was quoted from regulation (EU) No 10/2011.

2. Pentachlorophenol (PCP) Content

Test Item	Result (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
	No.1		
Pentachlorophenol (PCP)	ND	0.10	0.15

Note:

1. Test method: With reference to LFGB § 64 BVL B 82.02.8-2001, analysis was performed by GC-MS.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from Council of Europe Resolution AP(2002)1.

3. Overall Migration Test

Food Simulant	Test Condition	Result(mg/dm ²)	LOQ(mg/dm ²)	Limit(mg/dm ²)
		No.2		
3% Acetic Acid	70°C for 2 hours	ND	3	10
10% Ethanol	70°C for 2 hours	ND	3	10

Note:

1. Test method: With reference to BS EN 1186-1: 2002, BS EN 1186-3: 2002, BS EN 1186-9: 2002 and BS EN 1186-14: 2002.
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. "°C" = Celsius degree
4. LOQ = Limit of quantitation
5. ND = Not Detected or lower than limit of quantitation
6. The specification was quoted from Council of Europe Resolution AP (2004)5.

**4. Bisphenol A Content**

Test Item	Result (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
	No.2		
Bisphenol A	ND	0.1	Not Detected (<0.1mg/kg)

Note:

1. Test Method: With reference to EPA3550C:2007, analysis was performed by GC-MS.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from Law No 2012-1442.

Sample Photo:

**Photograph of parts tested:**

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Wood	Wood
2		Black silicone rubber	Silicone rubber

===== End of Report =====

WALTEK